# **INDUSTRY**



# CEPSA CIRCULANTE 500

# **DESCRIPTION**

Circulation oils formulated with highly refined paraffinic base oils and selective ash-free additivation that give them excellent characteristics for the type of service for which they are intended.

# **PRODUCT APPLICATIONS**

- Especially recommended for circulation systems in paper mills and in the steel industry.
- In Paper Factories: for dry-part bearings (ISO VG 220) and wet-part bearings (ISO VG 150) in compliance with the requirements stipulated by the main manufacturers of paper mill machinery.
- In the Steel industry: for Mesta and Morgoil thrust roller bearings for rolling mills.

#### **PRODUCT PERFORMANCE**

- Excellent emulsion-removing capacity even after long periods of service.
- Very good anti-foam properties.
- Highly resistant to oxidation. Long duration of service loads.
- Very good anti-corrosion and anti-rust properties. It ensures high protection for the parts of the machines in contact with the oil.
- The use of ash-free additivation gives it an excellent anti-wear capacity, which reduces the friction coefficients to the maximum, thereby avoiding temperature increases and reducing energy consumption.
- Extraordinary filterability characteristics.

# **SPECIFICATIONS**

SMS SIEMAG
MORGOIL
MESTA
DIN 51517 Parte 3 (CLP)

## TYPICAL CHARACTERISTICS

CHARACTERISTIC	UNITS	METHOD	CEPSA CIRCULANTE SERIAL 500				
DESCRIPTION			525	528	535	546	548
ISO GRADE			100	150	220	460	680
Density at 15 °C	Kg/l	ASTM D-4052	0.889	0.895	0.899	0.906	0.907
Flash Point, COC	oC	ASTM D-92	230	240	250	304	306
Freezing point, max.	oC	ASTM D-5950	-15	-12	-12	-9	-9
Viscosity at 40°C	cSt	ASTM D-445	97	151	245	468	611
Viscosity at 100°C	cSt	ASTM D-445	10.9	14.9	20.6	31.6	37.4
Viscosity index	-	ASTM D-2270	96	98	98	98	98
Demulsibility at 82°C, 3 ml	minutes	ASTM D-1401	<20	<30	<30	<30	<60
FZG test, failure stage	-	DIN 51354-2	12	12	12	12	12
Rust prevention (Proc. A)	-	ASTM D-665	Pass	Pass	Pass	Pass	Pass

## **HEALTH & SAFETY AND ENVIRONMENT**

Health, safety and environmental information is provided for this product in the Materials Safety Data Sheet. This gives details of potential hazards, precautions and First Aid measures together with environmental effects and disposal of used products.

The typical values of the characteristics appearing in the table are average values given for guidance purposes. These values may be modified without any prior warning.