

Asphalt bitumen 50/70 A

Asphalt bitumen with adhesion promoters, which complies with the specifications in the standard EN 12591 for 50/70 bitumen.

Applications:

- › Hot bituminous mixtures in which a better adhesion is required

Recommended working temperatures:

- › Mixing temperature (°C): 150- 160
- › Working temperature (°C): 150- 160
- › Compaction temperature (°C): 145- 155
- › Maximum heating temperature (°C): 170

Specifications:

Characteristics	Units	Standard	Min.	Max.
Fresh binder				
Penetration (25 °C)	0,1 mm	EN 1426	50	70
Softening point (R&B)	°C	EN 1427	46	54
Penetration index	-	EN 12591	-1,5	+0,7
Fraass point	°C	EN 12593	-	-8
Solubility	%	EN 12592	99,0	-
Flash point	°C	EN ISO 2592	230	-
RTFOT residue				
Mass loss	%	EN 12607-1	-	0,5
Retained penetration	% p.o.	EN 1426	50	-
Increase in softening point	°C	EN 1427	-	11



Revision No. 6 - Approved: 24/10/2025 - Next revision: 24/10/2030

For further information, please visit www.moeve.es/en/

N.B: The recommendations in these technical specifications are purely for guidance and for general situations and Moeve takes no responsibility whatsoever for misuse. For individual cases, contact Moeve Technical Department.