

Asphalt bitumen 50/70 BT

Asphalt bitumen designed for warm mix fabrication. It enables reducing fabrication temperatures as well as energy consumption and greenhouse gas emissions.

Applications:

- > Warm asphalt mixtures
- > Mixtures requiring long transportation time and/or implementation procedures
- > Conventional asphalt mixtures

Recommended working temperatures:

- > Mixing temperature (°C): 150- 160
- > Working temperature (°C): 150- 160
- > Compaction temperature (°C): 145- 155
- > Maximum heating temperature (°C): 170

Specifications:

Characteristics	Units	Standard	Min.	Max.
Fresh binder				
Penetration (25 °C; 100 g; 5s)	0,1 mm	EN 1426	50	70
Softening point	°C	EN 1427	46	54
Penetration index	-	EN 12591	-1,5	+0,7
Fraass point	°C	EN 12593	-	-8
Solubility	%	EN 12592	99,0	-
Flash point	°C	EN 2592	230	-
RTFOT residue				
Mass loss	%	EN 12607-1	-	0,5
Retained penetration	% p.o.	EN 1426	50	-
Variation in softening point	°C	EN 1427	-	11



Revision No. 6 - Approved: November 24th 2025 - Next review: November 24th 2030

For further information, please visit www.moeve.es/en/

N.B: The recommendations in these technical specifications are purely for guidance and for general situations and Moeve takes no responsibility whatsoever for misuse. For individual cases, contact Moeve Technical Department.